



Technical Data Sheet









Spectral EXTRA 715

Galvanized steel & aluminium adhesion increasing agent

RELATED PRODUCTS

PROPERTIES

- Improves adhesion to galvanized steel and aluminium
 - Extremely effective
 - Non-toxic
 - Odourless
 - Unique formula
- Environmentally safe

USE	
<ul style="list-style-type: none"> Galvanized steel Hot dip zinc coated steel Aluminium 	
VOC CONTENT	
VOC II/B/c limit	780 g/l
Actual VOC	0 g/l
PROCEDURE	
	Degrease the surface with Spectral EXTRA 785
	Apply EXTRA 715 on the surface and leave for 1 to 2 minutes
	Wipe the surface dry
	Wash the surface with Spectral EXTRA 785
 or 	Apply the main product (e.g. a putty or an acrylic filler)
	Adhesion development time (from product application): - 15 minutes for standard polyester putties - 2 h for the spray filler 1.5 h for Protect 380
	Start processing after that time to sand/process shown on the product's TDS.
STORAGE CONDITIONS	
Keep in dry rooms at above +10°C. Avoid direct exposure to sunlight. Reseal the container after use.	
SHELF LIFE	
Spectral EXTRA 715	12 months/20°C
SAFETY	
See the Safety Data Sheet.	
OTHER INFORMATION	
Registration number: 000024104. The effectiveness of our systems results from laboratory research and many years of experience. The data contained herein meets the current knowledge about our products and their application potential. We ensure high quality, provided the user follows the instructions and the work is performed in accordance with good workmanship. It is necessary to perform a test application of the product due to its potentially different reaction with different materials. We may not be held liable for defects if the final result was affected by factors beyond our control.	